

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 3/34, C08J 3/20	A1	(11) International Publication Number: WO 99/29767 (43) International Publication Date: 17 June 1999 (17.06.99)
(21) International Application Number: PCT/NL98/00702 (22) International Filing Date: 8 December 1998 (08.12.98) (30) Priority Data: 1007767 11 December 1997 (11.12.97) NL (71) Applicant (for all designated States except US): DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): KORBEE, Roland, Alexander [NL/NL]; Haagstraat 29, NL-6133 VR Sittard (NL). VAN GEENEN, Albert, Arnold [NL/NL]; Avond- sterstraat 20, NL-6133 Sittard (NL). (74) Agent: ALFENAAR, Marinus; Octrooibureau DSM, P.O. Box 9, NL-6160 MA Geleen (NL).		(81) Designated States: AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR THE PREPARATION OF A POLYAMIDE NANOCOMPOSITE COMPOSITION		
(57) Abstract <p>The invention relates to a process for the preparation of a polyamide nanocomposite composition by mixing in the melt phase a polyamide, a solid substance composed of anisotropic particles with a high aspect ratio and a liquid, the liquid being added to and subsequently mixed with a melt comprising at least the polyamide. Preferably water is chosen as the liquid. The invention also relates to a polyamide nanocomposite composition obtained by mixing in the melt phase a polyamide and a non-swollen solid substance composed of particles with a high aspect ratio. The polyamide nanocomposite compositions obtained with the process according to the invention and the polyamide nanocomposite compositions according to the invention can be used in all-moulded parts which can be produced with a polyamide composition and which demand particularly good mechanical properties, for example for use in the motor compartment of a vehicle, for casings and for connectors.</p>		

AM2

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

5 PROCESS FOR THE PREPARATION OF
 A POLYAMIDE NANOCOMPOSITE COMPOSITION

 The invention relates to a process for the
10 preparation of a polyamide nanocomposite composition by
 mixing in the melt phase a polyamide, a solid substance
 composed of anisotropic particles with a high aspect
 ratio and a liquid.

 In the context of the present application
15 'a nanocomposite composition' will be understood to be
 a mixture of two or more materials, the mixture at
 least comprising a first material being a polymer and a
 second material being anisotropic particles with a
 large aspect ratio having dimensions in the nanometre
20 area, the second material being dispersed in the first
 material, and the mixture possessing excellent
 mechanical properties, in particular a higher heat
 deflection temperature, impact resistance, stiffness
 and tensile strength and very good gas-diffusion
25 barrier properties, in comparison with a polyamide
 composition not comprising this second material.

 Such a process is known from EP-A-
 398.551 (Ube/Toyota). The process according to EP-A-
 398.551 is used to successively (a) preswell a clay in
30 the presence of water and 12-aminododecanoic acid, (b)
 further swell the preswollen clay in the presence of
 water and ϵ -caprolactam, (c) prepare a dispersion
 consisting of the swollen clay, water, ϵ -caprolactam

- 2 -

and nylon-6 and (d) melting and kneading the dispersion.

The process described in EP-A-398.551 involves the drawback that it is time-consuming because
5 the anisotropic particles with a high aspect ratio are introduced into the polyamide composition by first causing a swellable solid substance composed of anisotropic particles with a high aspect ratio that is available as a natural or synthetic raw material in
10 unswollen condition to swell before the mixture, comprising the swollen solid substance composed of anisotropic particles with a high aspect ratio, the polyamide and a liquid, is melted and kneaded. According to EP-A-398.551 the swelling is thus carried
15 out in two steps, in the presence of water and 12-aminododecanoic acid at 80°C for 60 minutes, and in the presence of water and ϵ -caprolactam for an unspecified time with constant stirring, respectively. The aim of effecting the swelling is to increase the distance
20 between the anisotropic particles with a high aspect ratio in the solid substance composed of these anisotropic particles so that the anisotropic particles are during the mixing in the melt phase released from the swellable solid substance and
25 dispersed in the melt.

An additional drawback of the process described in EP-A-398.551 is that it is necessary to use specific swelling agents, in this case 12-aminododecanoic acid and ϵ -caprolactam, which may give
30 rise to undesired side-reactions in the polymer melt, leading to, inter alia, an impure composition and consequently an inferior end product.

Another drawback of the process described in EP-A-398.551 is that liquids, more specifically dispersing agents and swelling agents, for example water, organic compounds or mixtures of water and organic compounds present in the mixture that is melted, escape as vapours during the melting, for example via the feed opening of an extruder, and consequently give rise to processing problems, for example in the melting and kneading of the melt, as a result of which a polyamide nanocomposite composition of inferior quality is obtained, in particular the composition is discoloured or it comprises gas pockets.

The invention's aim is to provide a process that comprises fewer steps and can hence be carried out more quickly, in which it is not necessary for the solid substance composed of anisotropic particles with a high aspect ratio to be swollen before the solid substance is mixed with a polyamide and in which no processing problems occur as a result of the presence of a liquid in the mixture that is melted.

This aim is achieved by adding the liquid to, and subsequently mixing it with a melt comprising at least the polyamide.

An additional advantage of the process according to the invention is that the melt, comprising at least the polyamide, the solid substance composed of anisotropic particles with a high aspect ratio and the liquid, can be kneaded and processed at a temperature lower than the polyamide's melting temperature. It was also found that the melt, consisting of at least the polyamide, the solid substance composed of anisotropic particles with a high aspect ratio and the liquid, has a viscosity that is lower than the viscosity of a melt

of the polyamide alone, as a result of which less energy need to be supplied to the mixing apparatus during the kneading and less shear heat is developed in the melt. As a result of the lowering of both the
5 melt's processing temperature and the melt's viscosity there is a smaller risk of gel formation or chain break-up during the mixing in the melt phase, as a result of which a better end product is obtained.

In principle, all the usual solvents or
10 mixtures thereof can be used as the liquid. Preferably a compound or mixture of compounds is chosen which is at least partly miscible with the polyamide in the melt phase or which is capable of causing a solid substance composed of anisotropic particles with a high aspect
15 ratio to swell. 'Mixtures' are in this context also understood to be mixtures comprising a compound that is a good swelling agent, but is poorly miscible with a polyamide melt, and a compound that is not a good swelling agent, but is well miscible with a polyamide
20 melt. The liquid is for example chosen from the group comprising water; aliphatic and cycloaliphatic hydrocarbons which may optionally be substituted, for example heptane, cyclohexane or dichloromethane; aromatic hydrocarbons which may optionally be
25 substituted, for example benzene, toluene, xylene, chlorobenzene, dichlorobenzene, trichlorobenzene or nitrobenzene; ethers, for example dioxane, diethyl ether or tetrahydrofuran; ketones, for example cyclohexanone or acetophenone; esters, for example
30 ethyl acetate or propiolactone; nitriles, for example acetonitrile or benzonitrile; alcohols, for example methanol, ethanol, n-propanol or isopropanol; or mixtures thereof. Particularly suitable is water or an

- 5 -

aqueous mixture of one or more of the aforementioned compounds. It has surprisingly been found that the process according to the invention using water as the liquid caused no substantial degradation of the polyamide, whereas it is nevertheless commonly known that a polyamide degrades at a temperature of more than 100°C in the presence of water, i.e. that chain break-up takes place, for example in an extruder, at a normal residence time of 2 to 4 minutes. Water is also - from an environmental viewpoint - a better choice for the liquid than for example an aromatic hydrocarbon.

The amount of liquid that can be used is not critical. The amount of liquid is preferably 5-50% by weight, more preferably 10-40% by weight, relative to the weight of the polyamide.

As the polyamide any polymer can be chosen that comprises acid-amide bonds (-CONH-) between the repeating units, more in particular polyamides or copolyamides obtained from ϵ -caprolactam, 6-aminocaproic acid, ω -enantholactam, 7-aminoheptanoic acid, 11-aminodecanoic acid, 9-aminononanoic acid, α -pyrrolidone or α -piperidone; polymers or copolymers obtained through the polycondensation of diamines, for example hexamethylene diamine, nonamethylene diamine, undecamethylene diamine, dodecamethylene diamine or metaxylene diamine, with dicarboxylic acids, for example terephthalic acid, isophthalic acid, adipic acid or sebacic acid; blends of the aforementioned polymers and copolymers. Examples of such polymers are nylon-6, nylon-9, nylon-11, nylon-12, nylon-4,6 and nylon-6,6. Preferably nylon-6 is chosen.

The polyamide preferably has an average molecular weight of between 9,000 and 40,000.

As the solid substance composed of anisotropic particles with a high aspect ratio a solid substance is preferably chosen from the group comprising layered and fibrous inorganic materials.

5 A particle's 'aspect ratio' is in the context of this invention understood to be the ratio of an individual particle's largest and smallest dimension. More in particular the aspect ratio of a plate is the ratio of the plate's length and average
10 thickness and the aspect ratio of a fibre is the ratio of the fibre's length and average diameter. Preferably a solid substance is chosen that is composed of anisotropic particles with a high aspect ratio, the aspect ratio lying between 5 and 10,000, preferably
15 between 10 and 10,000, more preferably between 100 and 10,000.

Suitable layered inorganic materials are composed of plates with an average aspect ratio of between 5 and 10,000, the plates having an average
20 thickness equal to or less than about 2.5 nm and a maximum thickness of 10 nm, preferably of between about 0.4 nm and about 2.5 nm, more preferably of between about 0.4 nm and about 2 nm. The average length of the plates is preferably between about 2 nm and 1,000 nm.
25 Examples of suitable layered inorganic materials are phyllosilicates, for example smectite clay minerals, vermiculite clay minerals and micas. Examples of suitable smectite clay minerals are montmorillonite, nontronite, beidellite, volkonskoite, hectorite,
30 stevensite, pyroysite, saponite, sauconite, magadiite and kenyaite. Preferably montmorillonite is chosen.

In the suitable fibrous inorganic materials the individual fibres have an average aspect

ratio of between 5 and 10,000, the individual fibres' diameter being equal to or smaller than about 10 nm, with a maximum diameter of 20 nm, preferably between about 0.5 nm and about 10 nm, more preferably between about 0.5 nm and about 5 nm. The average length of the individual fibres in suitable fibrous inorganic materials is usually equal to or smaller than about 2,000 nm, with a maximum length of about 10,000 nm, preferably between about 20 nm and about 200 nm, more preferably between about 40 nm and about 100 nm. Examples of suitable fibrous inorganic materials are imogolite and vanadium oxide.

The amount of solid substance composed of the anisotropic particles with a high aspect ratio can be freely chosen; the amount is dependent only on the desired properties of the polyamide nanocomposite composition to be obtained. Preferably an amount is chosen of between 0.05 % by weight and 30 % by weight, relative to the polyamide.

The polyamide nanocomposite composition optionally comprises other polymers, but the amount of these other polymers must be chosen so that they do not interfere with the execution of the invention. Examples of such polymers are polypropylene (PP), acrylonitrile-butadiene-styrene (ABS), polyphenylene oxide (PFO), polycarbonate (PC), polyethylene terephthalate (PET) and polybutylene terephthalate (PBT).

The polyamide nanocomposite composition optionally comprises additives, for example fillers and reinforcing materials, for example glass fibres and silicates, for example talcum, flame retardants, foaming agents, stabilisers, flow-promoting agents and pigments.

Although the process according to the invention is particularly suitable for the preparation of a nanocomposite composition by mixing in the melt phase a polyamide, a non-swollen solid substance
5 composed of anisotropic particles with a high aspect ratio and a liquid, the invention is not impeded by the fact that the process can also be carried out using a swollen solid substance composed of the anisotropic particles with a high aspect ratio, in which case the
10 swelling can be effected in any manner known to a person skilled in the art, for example as described in EP-A-398,551.

To mix the liquid with the polyamide melt, use is preferably made of a mixing device fitted with
15 means for adding a liquid to the melt in a controlled manner and for preventing the escape of the liquid during the mixing and kneading process. The mixing device may also be fitted with means for allowing the liquid to escape in a controlled manner, for example
20 before the melt leaves the mixing device.

In a preferred embodiment the melt, which comprises at least the polyamide, also already comprises the solid substance composed of anisotropic particles with a high aspect ratio before the liquid is
25 mixed with the melt.

In a second preferred embodiment the solid substance composed of anisotropic particles with a high aspect ratio is dispersed in the liquid and the dispersion thus obtained is mixed with the polymer
30 melt, which comprises at least the polyamide.

A mixed form of the aforementioned two preferred embodiments can of course also be used.

Any method known to a person skilled in the art can be used to mix the melt, more in particular a method that exerts shear forces on a polymer melt. Preferably the mixing is effected with the aid of the equipment usually used for mixing a polymer melt, for example stirrers, Banbury-type mixers, Brabender-type mixers, continuous mixers or extruders. Preferably an extruder is used. In a preferred embodiment an extruder is used that is successively fitted with a melting part, a contra-rotating part, an injection gate for adding water, a second contra-rotating part and a degassing gate. In the zone between the two contra-rotating parts the water is mixed with the polymer melt and the solid substance composed of anisotropic particles with a high aspect ratio under pressure and at an elevated temperature. The pressure in this zone is typically 1-1.5 MPa. It is important that the liquid cannot substantially escape from the mixing zone during the mixing. The melt is preferably kneaded at a pressure of more than 1 atmosphere and at a temperature lower than the polyamide's melting temperature. The water can optionally be removed from the melt in its entirety or in part before the composition leaves the mixing apparatus, for example via a degassing gate in an extruder that is for example operated at lowered pressure.

The invention also relates to a polyamide nanocomposite composition obtained by mixing in the melt phase a polyamide and a non-swollen solid substance composed of particles with a high aspect ratio. From EP-A-398.551 (Ube/Toyota) a polyamide nanocomposite composition is known that has been obtained by mixing a swollen montmorillonite clay in

- 10 -

the melt phase with nylon-6 (Table 1, Comparative Example A). A drawback of this composition is that the solid substance has to be swollen before being mixed with the melt. Also known from EP-A-398.551 is a composition by mixing in the melt phase a non-swollen montmorillonite clay and nylon-6 (Table 1, Comparative Example B). The montmorillonite plates are not dispersed in this composition and the composition has properties that are not better than those of a similar composition without the montmorillonite clay, in particular a Heat Distortion Temperature (HDT) that does not differ appreciably from that of a commercially available nylon-6 (Table 1, Comparative Example C). The polyamide nanocomposite composition according to the invention however has a HDT that is comparable with the HDT of the polyamide nanocomposite composition according to EP-A-398.551. The polyamides and solid substances and their amounts described above in this patent can be chosen as the polyamide and the solid substance comprising the anisotropic particles with a high aspect ratio, respectively.

The polyamide nanocomposite compositions obtained with the process according to the invention and the polyamide nanocomposite compositions according to the invention can be used in all moulded parts which can be produced with a polyamide composition and which demand particularly good mechanical properties, for example for use in the motor compartment of a vehicle, for casings and for connectors.

The invention will now be elucidated with reference to examples, without being limited hereto.

EXAMPLESExample I and Comparative Examples A, B and C

Nylon-6 (Akulon K123, DSM N.V.) was
5 cryogenically ground to a particle size of < 1 mm. 4750
g of the ground nylon-6 and 250 g of montmorillonite
clay (Kunipia F, Kunimine Industries) were mixed in a
tumbler. The (dry) powder mixture was dosed to a ZSK
twin-screw extruder (Werner & Pfleiderer) having a
10 screw diameter of 30 mm and a length/diameter ratio of
39. The screw was fitted with, successively (from the
feed opening), a melting part, a contra-rotating part,
an injection gate for the introduction of water, a
second contra-rotating part and a degassing gate. The
15 extruder temperature was set to a value varying from
190 to 215°C over the entire length of the cylinder,
which is lower than the melting temperature of the
nylon-6. The dry clay/nylon mixture was continuously
fed to the extruder at a throughput of 4 kg per hour.
20 Water was injected into the melt at a throughput of 20
g per minute (which corresponds to about 30 % by weight
of water, relative to the nylon-6). The water that was
injected into the melt was discharged via the degassing
gate at the end of the extruder at a pressure varying
25 from 3 to 6 kPa. The polyamide nanocomposite
composition was extruded as a strand which was cooled
in water. The strand was chopped into granules with a
length of approx. 3 mm and a diameter of approx. 2 mm.
A film was pressed from the polyamide nanocomposite
30 composition thus obtained, tested for Rheometric Strain
Analysis (RSA), a technique with which the modulus of
elasticity is measured as a function of the
temperature. The Heat Distortion Temperature (HDT) was

inferred from the RSA measurement and is indicated in Table 1. Also included in this table are the HDT values of a commercial grade of nylon-6 polyamide (Akulon K123, DSM N.V.) and of a polyamide composition prepared using swollen and non-swollen montmorillonite according to EP-A-398.551, (Example 1 and Comparative Example 7).

From Table 1 it is clear that the composition prepared according to the invention (Example I) has a comparable HDT as the composition prepared according to the state of the art (example A). Also, it is shown that the composition according to the invention (Example I) outperforms the composition according to the state of the art (Example B).

Transmission Electron Microscopy (TEM) photographs were made of a cross-section of a slice (thickness 70 nm) of a granule of the polyamide nanocomposite composition of Example I (Fig. 1: enlarged 19,000 x, scale bar = 2 micrometres; Fig. 2: enlarged 99,000 x, scale bar = 500 nm). In the photos it can be seen that the montmorillonite clay plates are homogeneously dispersed in the nylon-6 matrix, which proves the effectiveness of the measures according to our invention to produce a nanocomposite composition.

Table 1 : Polyamide nanocomposite compositions

	Example I	Comparative Example A	Comparative Example B	Comparative Example C
Polymer	Nylon-6 nanocomposite according to the invention	Nylon-6 nanocomposite (EP-A-398.551, Example 1)	Nylon-6 Composition (EP-A-398.551, Comparative Example 7)	Nylon-6 Akulon K123 (DSM N.V.)
Clay	non-swollen montmorillonite	swollen montmorillonite	non-swollen montmorillonite	none
Clay (% by weight)	5	5.3	2	0
HDT (°C)	152	163	92	96

C L A I M S

1. Process for the preparation of a polyamide
5 nanocomposite composition by mixing in the melt phase a polyamide, a solid substance composed of anisotropic particles with a high aspect ratio and a liquid, characterised in that the liquid is added to and subsequently mixed with a melt which
10 comprises at least the polyamide.
2. Process according to Claim 2, characterised in that the melt, which comprises at least the polyamide, also comprises the solid substance composed of anisotropic particles with a high
15 aspect ratio before the liquid is mixed with the melt.
3. Process according to Claim 1, characterised in that the liquid comprises the solid substance composed of anisotropic particles with a high
20 aspect ratio.
4. Process according to any one of Claims 1-3, characterised in that water is chosen as the liquid.
5. Process according to any one of Claims 1-4,
25 characterised in that the amount of liquid is preferably 5-50% by weight, more preferably 10-40% by weight, relative to the weight of the polyamide.
6. Process according to any one of Claims 1-5,
30 characterised in that nylon-6 is chosen as the polyamide.

- 15 -

7. Process according to any one of Claims 1-6, characterised in that the anisotropic particles have an aspect ratio of between 5 and 10,000.
8. Process according to any one of Claims 1-7, characterised in that the solid substance that is composed of anisotropic particles with a high aspect ratio is chosen from the group comprising layered and fibrous inorganic materials.
9. Process according to Claim 8, characterised in that montmorillonite is chosen as the layered inorganic material.
10. Process according to any one of Claims 1-9, characterised in that the amount of solid substance equals 0.05 - 30% by weight, relative to the polyamide.
11. Process according to any one of Claims 1-10, characterised in that the solid substance that is composed of anisotropic particles with a high aspect ratio is not swollen.
12. Process according to any one of Claims 1-11, characterised in that the liquid is mixed with the melt under pressure.
13. Process according to any one of Claims 1-12, characterised in that the mixing in the melt phase is effected with the aid of an extruder.
14. Process according to Claim 13, characterised in that the extruder is successively fitted with at least a melting part, a contra-rotating part, an injection gate for introducing the liquid, a second contra-rotating part and a degassing gate.
15. Polyamide nanocomposite composition obtained with the process according to any one of Claims 1-14.

16. Polyamide nanocomposite composition obtained by mixing in the melt phase a polyamide and a non-swollen solid substance composed of particles with a high aspect ratio.
- 5 17. Moulded part consisting of at least a polyamide nanocomposite composition obtained using a process according to any one of Claims 1-14.
18. Moulded part consisting of at least a polyamide nanocomposite composition according to any one of
- 10 Claims 15-16.
19. Process for the preparation of a polyamide nanocomposite composition and a polyamide nanocomposite composition as described and elucidated with reference to the examples.




FIG 1




FIG 2

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 98/00702

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08K3/34 C08J3/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 358 415 A (UBE INDUSTRIES ; TOYOTA MOTOR CO LTD (JP); TOYODA CHUO KENKYUSHO KK) 14 March 1990 ---	
A	US 4 894 411 A (OKADA AKANE ET AL) 16 January 1990 ---	
A	EP 0 398 551 A (UBE INDUSTRIES ; TOYOTA MOTOR CO LTD (JP); TOYODA CHUO KENKYUSHO KK) 22 November 1990 cited in the application ---	
A	US 4 739 007 A (OKADA AKANE ET AL) 19 April 1988 -----	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

25 January 1999

Date of mailing of the international search report

05/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Leroy, A

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 98/00702

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0358415 A	14-03-1990	JP 2069562 A	08-03-1990
		JP 7039540 B	01-05-1995
		JP 2102261 A	13-04-1990
		JP 8019230 B	28-02-1996
		JP 2105856 A	18-04-1990
		JP 2603314 B	23-04-1997
		JP 2173160 A	04-07-1990
		JP 2565557 B	18-12-1996
		DK 439889 A	07-03-1990
		FI 894148 A	07-03-1990
		US 5248720 A	28-09-1993
US 4894411 A	16-01-1990	JP 2519045 B	31-07-1996
		JP 63230766 A	27-09-1988
		JP 1011157 A	13-01-1989
		JP 2572234 B	16-01-1997
		DE 3808623 A	06-10-1988
EP 0398551 A	22-11-1990	JP 2305828 A	19-12-1990
		JP 7047644 B	24-05-1995
		DE 69023542 D	21-12-1995
		DE 69023542 T	20-06-1996
		US 5102948 A	07-04-1992
US 4739007 A	19-04-1988	JP 62252425 A	04-11-1987
		JP 8022946 B	06-03-1996
		JP 62074957 A	06-04-1987
		DE 3632865 A	02-04-1987